

## Granular Activated Carbon

(минеральный гранулированный активированный уголь)



# Silcarbon S30-60

### Technical Data Sheet

Appearance:	granular carbon	
Apparent density:	0.45 – 0.03 kg/l	ASTM D 2854
Particle size:	30 x 60 mesh 0.25 – 0.6 mm	ASTM D 2862
Water content, as packed:	10 % max.	ASTM D 2867
Ash content:	12 % max.	ASTM D 2866
Iodine number:	1,000 mg/g min.	AWWA B604-74
Surface area:	1,050 m <sup>2</sup> /g min.	BET method
CCl <sub>4</sub> number:	60 % min.	ASTM D 3467
Ball pan hardness:	95 % min.	ASTM D 3802
Standard packing:	25 kg bags. Other packing units are available on request.	

**Закажите активированный уголь Silcarbon**

**[www.silcarbon.ru](http://www.silcarbon.ru)**

8-911-736-63-88 ООО «Индига», Алексей Денисов

факс 8-812-309-25-99

[info@silcarbon.ru](mailto:info@silcarbon.ru)

